

Product Data Sheet

SUMITOMO POLYAMIDE

S3200

Polyamide-6, High Viscosity

Applications	Industrial applications, barrier films, and high tenacity filaments for fishing net and tyre cord.
Characteristics	High viscosity. Contains no lubrication.
Typical Processing Conditions	Extrusion temperature : 240°C - 300°C

Typical Properties

Physical		Value	Unit	Method
Relative Viscosity		3.20	-	ISO 307
Density		1.12	g/cm ³	ASTM D792
Water Content		< 0.06	wt%	ASTM D6869
Water Absorption	23°C in water	11.1	%	ISO 62
Extractable Content		< 0.5	wt%	Internal
Amino End Group		35 - 45	meq/kg	Internal
Chip Count		70 - 110	pcs/g	Internal
Mechanical		Value (Dry)	Unit	Method
Tensile Strength	at Yield	80	MPa	ASTM D638
Tensile Elongation	at Yield	4	%	ASTM D638
	at Break	87	%	ASTM D638
Tensile Modulus		2750	MPa	ASTM D638
Flexural Strength		104	MPa	ASTM D790
Flexural Modulus		2650	MPa	ASTM D790
Impact Strength, Izod	notched, 23°C	6	kJ/m ²	ASTM D256
Hardness	R Scale	119	-	ASTM D785-03
Thermal		Value	Unit	Method
Heat Deflection Temperature	1.80MPa	57	°C	ASTM D648
Melting Temperature		220	°C	ASTM D3418
Other		Value	Unit	Method
UL Flammability		HB	-	UL94/1.6mm

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary
 RV measured using 1% (w/v) in 96% (w/w) sulfuric acid

Manufacturer

S3200 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh). Petro Rabigh is an ISO 9001, ISO 14001, and ISO 45001 certified company.

Regulatory Compliances

Unmodified S3200 complies with the requirements of,

- US FDA Regulation 21 CFR 177.1500 and its amendments
- EU Commission Regulation 10/2011 (PIM) and its amendments

Please contact your nearest SCA representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2011/65/EC, and its amendments, on RoHS in electrical and electronic equipment are not used in the manufacturing process, and are therefore not expected to be present in the product.

Storage and Handling

S3200 is supplied pre-dried in moisture-proof 25kg bags or 730kg jumbo bags with aluminium liner. It is advisable to store in a well-ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust. Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odour characteristic of the resin.

It is recommended to process S3200 within 6 months upon receipt.

Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritises environmental management in all our operations in responsibility and respect towards the community and the environment.

Disposal of S3200 should at all times comply with the local and regional environmental protection and waste disposal regulations.

Office Locations**SUMITOMO CHEMICAL ASIA PTE LTD**

3 Fraser Street, #07-28 DUO Tower, SINGAPORE 189352

Phone +65 6303 5188

Fax +65 6298 9621

Web Site www.sumitomo-chem.com.sg

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

1607, Ascendas Plaza, 333 Tian Yao Qiao Road, Xu Hui District, Shanghai, CHINA 200030

Phone +86 21 6448 2255

Fax +86 21 6407 7365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD., GUANGZHOU BRANCH

Room 6404, Office Building, CITIC Plaza, No.233, North Tianhe Road, Guangzhou City, CHINA 510613

Phone +86 20 3877 3577

Fax +86 20 3877 3511

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen, BELGIUM

Phone +32 2 251 0650

Fax +32 2 251 2991

Web Site sumitomochemicalseurope.eu

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Barbaros Mah. Cigdem Sok. No:1, Agaoglu My Office K:10, D:44-45, 34746 Bati Atasehir, Istanbul, TURKEY

Phone +90 216 680 3334

Fax +90 216 680 1012

Disclaimer

All information contained in this document is provided in good faith and its sole purpose is to provide information regarding SCA's polymer products. This product catalogue is provided on an "as is" basis. SCA makes no representation, warranty, express or implied and assumes no liability as to the accuracy or completeness of any of the information contained in this product catalogue. The values shown are purely values measured on the product and are not to be considered as guaranteed specifications. Any information on this product catalogue should not be considered as a recommendation. Customer is responsible to ensure that SCA materials, whether used alone or mix with other materials, are suitable for the intended application. SCA expressly disclaims for any and all liability, including direct and indirect loss, consequential loss or damages based on or relating to the use or errors of and omissions of such information in this product catalogue. Information contained herein is NOT intended to announce product availability anywhere in the world. Please contact your nearest SCA representative for more detailed information.